

Later 4 G/30

Polybutylene Terephthalate

LATI S.p.A.

Message:

Compound based on Polybutylene Terephthalate (PBT).

Glass fibres. Product UL certified.

General Information			
UL YellowCard	E54080-244034		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Density	1.52	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	1.0 to 1.3	%	
Flow : 2.00 mm	0.30 to 0.55	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2/1
23°C	10500	MPa	
60°C	6900	MPa	
90°C	5100	MPa	
120°C	4100	MPa	
150°C	3200	MPa	
Tensile Stress			ISO 527-2/5
Break, 23°C	125	MPa	
Break, 60°C	85.0	MPa	
Break, 90°C	70.0	MPa	
Break, 120°C	50.0	MPa	
Break, 150°C	45.0	MPa	
Tensile Strain			ISO 527-2/5
Break, 23°C	2.0	%	
Break, 60°C	2.8	%	
Break, 90°C	3.0	%	
Break, 120°C	3.1	%	
Break, 150°C	3.1	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	4.0	kJ/m ²	
23°C	4.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-20°C	35	kJ/m ²	

23°C	30	kJ/m ²	
Notched Izod Impact (23°C, 3.20 mm)	45	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
Continuous Use Temperature ²	140	°C	
Vicat Softening Temperature	210	°C	ISO 306/B50
CLTE - Flow (30 to 100°C)	1.5E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	HB		
1.50 mm	HB		
3.00 mm	HB		
Oxygen Index	23	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	110 to 130	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	240 to 250	°C	
Mold Temperature	70.0 to 90.0	°C	
Injection Rate	Moderate		
NOTE			
1.	at 60 MPa of cavity pressure		
2.	20,000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

