

E-RIALGLASS H 02 S 30 G

Polypropylene Homopolymer

RIALTI Srl

Message:

Polypropylene homopolymer obtained by industrial scraps recycling; 30% glass fiber reinforced, chemically coupled; thermal stabilization of process; good thermal and mechanical properties.

Flowability rate specific for extrusion and injection molding. Available in black versions.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Chemical Resistance		
	Good Flow		
	Good Thermal Stability		
	Homopolymer		
Appearance	Black		
Forms	Regrind		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.2	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.2	%	
Flow	0.40	%	
Ash Content	30	%	ISO 3451
Accelerated Oven Aging (150°C)	4.2	day	ISO 4577
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	80		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/20
Yield, 23°C	75.0	MPa	
Break, 23°C	75.0	MPa	
Tensile Strain (Break, 23°C)	2.5	%	ISO 527-2/20
Flexural Modulus ¹ (23°C)	5800	MPa	ISO 178
Flexural Stress (23°C)	109	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	35	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength			ISO 180/1A

-20°C	6.5	kJ/m ²	
23°C	8.5	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	140	°C	ISO 75-2/A
Vicat Softening Temperature	130	°C	ISO 306/B50
Ball Pressure Test (125°C)	Pass		IEC 335
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	210 to 250	°C	
Mold Temperature	40.0 to 60.0	°C	
Injection Rate	Fast		
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

