LARIPUR® LPR 5450

Thermoplastic Polyurethane Elastomer (Polyether)

COIM S.p.A.

Message:

LARIPUR®LPR 5450 is a thermoplastic polyurethane elastomer (polyether) (TPU-polyether) material. This product is available in North America, Latin America or Europe. The processing method is injection molding.

LARIPUR® The main features of LPR 5450 are:

high hardness Good tear strength Good toughness Impact resistance good weather resistance

General Information							
Features	Good tear strength Good wear resistance Low temperature impact resistance Good chemical resistance Good weather resistance Good toughness High hardness						
				Forms	Particle Particle		
				Processing Method	Injection molding		
				Physical	Nominal Value	Unit	Test Method
				Specific Gravity	1.18	g/cm³	ASTM D792
				Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	53		ASTM D2240				
Mechanical	Nominal Value	Unit	Test Method				
Flexural Modulus	159	МРа	ASTM D790				
Elastomers	Nominal Value	Unit	Test Method				
Tensile Stress			ASTM D412				
50% strain	11.6	МРа	ASTM D412				
100% strain	14.1	MPa	ASTM D412				
300% strain	36.4	MPa	ASTM D412				
Tensile Strength (Break)	60.8	MPa	ASTM D412				
Tensile Elongation (Break)	450	%	ASTM D412				
Tear Strength	150	kN/m	ASTM D624				
Thermal	Nominal Value	Unit	Test Method				
Vicat Softening Temperature	104	°C	ASTM D1525				
Additional Information							

Abrasion loss, DIN 53516: 40 mm³Tosion Test, ASTM D 1043, 20° C: 37 MPaTosion Test, ASTM D 1043, -20° C: 170 MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

