Carbotex KG-20MRA

Polycarbonate

Kotec Corporation

Message:

Carbotex KG-20MRA is a Polycarbonate (PC) product filled with 20% glass fiber. It is available in Africa & Middle East, Europe, Latin America, or North America

Characteristics include:

Flame Rated

Good Mold Release

High Viscosity

Mold Release Agent

| General Information | | | |
|--|----------------------------------|---------|-------------|
| UL YellowCard | E146413-223407 | | |
| Filler / Reinforcement | Glass Fiber,20% Filler by Weight | | |
| Additive | Mold Release | | |
| Features | Good Mold Release | | |
| | High Viscosity | | |
| Appearance | Natural Color | | |
| Forms | Pellets | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.35 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow | 0.30 to 0.50 | % | ASTM D955 |
| Water Absorption (23°C, 24 hr) | < 0.20 | % | ASTM D570 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 108 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 4.0 | % | ASTM D638 |
| Flexural Modulus | 5690 | MPa | ASTM D790 |
| Flexural Strength | 152 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C, 3.18 mm) | 90 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 145 | °C | ASTM D648 |
| Electrical | Nominal Value | Unit | Test Method |
| Volume Resistivity | 1.0E+16 | ohms·cm | ASTM D257 |
| Dielectric Strength (1.60 mm) | 20 | kV/mm | ASTM D149 |
| Dielectric Constant (1 MHz) | 3.20 | | ASTM D150 |
| Dissipation Factor (1 MHz) | 8.0E-3 | | ASTM D150 |
| Arc Resistance | 110 | sec | ASTM D495 |
| Flammability | Nominal Value | Unit | Test Method |

| Flame Rating (3.00 mm) | V-0 | UL 94 |
|------------------------|---------------|-------------|
| Optical | Nominal Value | Test Method |
| Haze (3.00 mm) | Translucent | ASTM D1003 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

