

ALCUDIA® LDPE 2303FL

Low Density Polyethylene
REPSOL

Message:

ALCUDIA® 2303-FL is stabilized with Ni quencher (yellow greenish colour), UV absorber and antioxidants. This compound offers high solar radiation resistance.

APLICACIONES

Films for greenhouses and tunnels cover.

ALCUDIA® 2303-FL, 180 µm thickness films, have a lifetime of two continuous agricultural seasons (two winters and one summer) in geographical areas where the maximum solar radiation is 160 kLy.

For further information, contact to Technical Assistance and Development Department or Commercial Attention Service.

Recommended melt temperature range from 190 to 210°C. Processing conditions should be optimised for each production line.

General Information			
Additive	Ni Quencher		
	Antioxidation		
	UV stabilizer		
Features	Antioxidation		
	Good UV resistance		
Uses	Films		
	Agricultural application		
Processing Method	Film extrusion		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.923	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.30	g/10 min	ISO 1133
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	180	µm	
Tensile Stress			ISO 527-3
MD: Fracture, 180 µm, blown film	19.0	MPa	ISO 527-3
TD: Fracture, 180 µm, blown film	19.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Fracture, 180 µm, blown film	500	%	ISO 527-3
TD: Fracture, 180 µm, blown film	600	%	ISO 527-3
Dart Drop Impact (180 µm, blown film)	750	g	ISO 7765-1
Elmendorf Tear Strength			ISO 6383-2
MD: 180 µm, blown film	6.0	N	ISO 6383-2
TD: 180 µm, blown film	9.0	N	ISO 6383-2
Optical	Nominal Value	Unit	Test Method
Haze (180 µm, blown film)	22	%	ASTM D1003

Global Transmission of Visible Light ¹ (180.0 μm)	90	%	EN 13206
Additional Information			
Data taken from 180 μm thickness film, blown up ratio 2.25:1.			
Extrusion	Nominal Value	Unit	
Melt Temperature	190 - 210	°C	
NOTE			
1.	Blown Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT