

# Santoprene™ 121-85M100

Thermoplastic Vulcanizate

ExxonMobil Chemical

## Message:

It is a hard, black, UV-resistant thermoplastic vulcanized elastomer (TPV) in the thermoplastic elastomer (TPE) series. This material has good physical properties and chemical resistance at the same time, and is used in fields that are difficult to injection molding. This brand of Shanduping TPV is a shear rate dependent product that can be processed on conventional thermoplastic injection molding equipment. This is a polyolefin-based material that can be recycled in the production process.

| General Information |                                 |                   |             |
|---------------------|---------------------------------|-------------------|-------------|
| UL YellowCard       | E80017-250511                   |                   |             |
| Features            | Good dimensional stability      |                   |             |
|                     | Good UV resistance              |                   |             |
|                     | Recyclable materials            |                   |             |
|                     | Good formability                |                   |             |
|                     | High liquidity                  |                   |             |
|                     | Ozone resistance                |                   |             |
|                     | Good chemical resistance        |                   |             |
|                     | Fatigue resistance              |                   |             |
|                     | Excellent appearance            |                   |             |
| Uses                | Parts under the hood of a car   |                   |             |
|                     | Application in Automobile Field |                   |             |
|                     | Car interior equipment          |                   |             |
|                     | Car exterior decoration         |                   |             |
|                     | Outdoor application             |                   |             |
| Agency Ratings      | UL QMFZ2                        |                   |             |
|                     | UL QMFZ8                        |                   |             |
| RoHS Compliance     | RoHS compliance                 |                   |             |
| UL File Number      | E80017                          |                   |             |
| Appearance          | Black                           |                   |             |
| Forms               | Particle                        |                   |             |
| Processing Method   | Multiple injection molding      |                   |             |
|                     | Injection molding               |                   |             |
| Physical            | Nominal Value                   | Unit              | Test Method |
| Specific Gravity    |                                 |                   |             |
| --                  | 0.908                           | g/cm <sup>3</sup> | ASTM D792   |
| --                  | 0.910                           | g/cm <sup>3</sup> | ISO 1183    |

| Hardness                                                                                                                                                                                  | Nominal Value                        | Unit        | Test Method        |
|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------------------------|-------------|--------------------|
| Durometer Hardness (Shaw A, 15 seconds, 23°C, 2.00mm)                                                                                                                                     | 91                                   |             | ISO 868            |
| Elastomers                                                                                                                                                                                | Nominal Value                        | Unit        | Test Method        |
| Tensile Stress - Across Flow (100% Strain, 23°C)                                                                                                                                          | 4.80                                 | MPa         | ASTM D412, ISO 37  |
| Tensile Strength - Across Flow (Break, 23°C)                                                                                                                                              | 7.30                                 | MPa         | ASTM D412, ISO 37  |
| Tensile Elongation - Across Flow (Break, 23°C)                                                                                                                                            | 390                                  | %           | ASTM D412, ISO 37  |
| Tear Strength - Across Flow                                                                                                                                                               |                                      |             |                    |
| 23°C <sup>1</sup>                                                                                                                                                                         | 31.0                                 | kN/m        | ASTM D624          |
| 23°C <sup>2</sup>                                                                                                                                                                         | 31                                   | kN/m        | ISO 34-1           |
| Compression Set                                                                                                                                                                           |                                      |             |                    |
| 70°C, 22 hr <sup>3</sup>                                                                                                                                                                  | 53                                   | %           | ASTM D395B         |
| 125°C, 70 hr <sup>4</sup>                                                                                                                                                                 | 62                                   | %           | ASTM D395B         |
| 70°C, 22 hr <sup>5</sup>                                                                                                                                                                  | 53                                   | %           | ISO 815            |
| 125°C, 70 hr <sup>6</sup>                                                                                                                                                                 | 62                                   | %           | ISO 815            |
| Aging                                                                                                                                                                                     | Nominal Value                        | Unit        | Test Method        |
| Change in Tensile Strength in Air (150°C, 168 hr)                                                                                                                                         | 3.0                                  | %           | ASTM D573, ISO 188 |
| Change in Ultimate Elongation in Air (150°C, 168 hr)                                                                                                                                      | -24                                  | %           | ASTM D573, ISO 188 |
| Change in Durometer Hardness in Air (Shore A, 150°C, 168 hr)                                                                                                                              | 1.0                                  |             | ASTM D573, ISO 188 |
| Thermal                                                                                                                                                                                   | Nominal Value                        | Unit        | Test Method        |
| Brittleness Temperature                                                                                                                                                                   | -54.0                                | °C          | ASTM D746, ISO 812 |
| Flammability                                                                                                                                                                              | Nominal Value                        | Test Method |                    |
| Flame Rating (1.10 mm)                                                                                                                                                                    | HB                                   | UL 94       |                    |
| Additional Information                                                                                                                                                                    |                                      |             |                    |
| 如果适用,这是基于扇形浇口注塑成型的平板测试结果.拉伸强度,伸长率和拉伸应力沿垂直流动方向测定 - ISO 1 型,ASTM die C.25%形变时的永久压缩变形.撕裂强度 - DIN 53515,die C(带缺口).从埃克森美孚欧洲分支机构直接购买的所有产品都符合 REACH 法规. 对于埃克森美孚未进口至欧洲的产品,用户应自行评估其是否满足 REACH 法规. |                                      |             |                    |
| Legal statement                                                                                                                                                                           |                                      |             |                    |
| 未经埃克森美孚化工书面允许,这种产品包括其产品名称,不得在任何医疗应用领域予以使用或有关详细的产品监管信息,请联系客户服务.                                                                                                                            |                                      |             |                    |
| Injection instructions                                                                                                                                                                    |                                      |             |                    |
| Santoprene TPV与乙缩醛和PVC不相容.更多关于加工和模具设计的信息,请查阅我们的《注射成型指南》.                                                                                                                                  |                                      |             |                    |
| NOTE                                                                                                                                                                                      |                                      |             |                    |
| 1.                                                                                                                                                                                        | C mould                              |             |                    |
| 2.                                                                                                                                                                                        | Method B, right-angle specimen (cut) |             |                    |
| 3.                                                                                                                                                                                        | Type 1                               |             |                    |
| 4.                                                                                                                                                                                        | Type 1                               |             |                    |
| 5.                                                                                                                                                                                        | Type a                               |             |                    |
| 6.                                                                                                                                                                                        | Type a                               |             |                    |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

