

Latilub 62-01M G/30

Polyamide 6

LATI S.p.A.

Message:

Self-lubricating product based on Polyamide 6 (PA 6).
Molybdenum disulfide. Glass fibres. Product UL certified.

General Information			
UL YellowCard	E54080-243982		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Molybdenum Disulfide Lubricant		
Features	Self Lubricating		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.75 to 1.0	%	
Flow : 2.00 mm	0.40 to 0.55	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	8800	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	160	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	%	ISO 527-2/5
Coefficient of Friction			ASTM D3702
vs. Itself - Dynamic	0.38		
vs. Itself - Static	0.45		
Wear Factor	3.10E-9	(m ³ /h)/(N·m·h)	ASTM D3702
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	70	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C, 3.20 mm)	85	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
Vicat Softening Temperature	210	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	240 to 280	°C	

Mold Temperature	70.0 to 100	°C
Injection Rate	Moderate	
NOTE		

1. at 60 Mpa of cavity pressure

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

