

ESTOPLAST EP 5230NN01

Polybutylene Terephthalate

Ester Industries Ltd.

Message:

Polybutylene Terephthalate - Glass Fiber Reinforced, 30%

Automotive: Interior parts, Connectors, Housings

Electrical & Electronic: Bobbins, Ignition Coil and Electrical Enclosure

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	Impact modifier		
Features	Impact modification		
Uses	Electrical/Electronic Applications		
	Connector		
	Application in Automobile Field		
	Car interior parts		
	Shell		
	spool		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.47	g/cm ³	ASTM D792
Water Absorption			ISO 62
Saturated, 23°C	0.50	%	ISO 62
Equilibrium, 23°C, 50% RH	0.25	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	110	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Strength	185	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	100	J/m	ASTM D256A
Unnotched Izod Impact (23°C)	800	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	205	°C	ASTM D648
1.8 MPa, not annealed	185	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.5 mm)	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	110 - 120	°C
Drying Time	3.0 - 4.0	hr
Rear Temperature	235 - 240	°C
Middle Temperature	250 - 260	°C
Nozzle Temperature	250 - 260	°C
Processing (Melt) Temp	240 - 250	°C
Mold Temperature	80 - 110	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

