

Styropor® P 426 C

Expanded Polystyrene

BASF Corporation

Message:

Application

For the production of expanded foam moldings having a wall thickness of at least 6 mm at particularly short cycle times.

Product description

Expandable polystyrene (EPS) (blowing agent: pentane).

General Information		
Additive	Blowing Agent 2	
Features	Fast Molding Cycle	
Uses	Foam	
Agency Ratings	EC 1907/2006 (REACH)	
RoHS Compliance	RoHS Compliant	
Forms	Spheres	
Physical	Nominal Value	Unit
Apparent Density	0.02	g/cm ³
Sieve Analysis		
< 300.0 µm	< 3.0	%
300.0 to 800.0 µm	> 92	%
> 800.0 µm	< 5.0	%
Aging - intermediate	4.0 to 24.0	hr
Bead Size	400.0 to 700.0	µm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT