

# CoREZYN® CORVE8300-35

Vinyl Ester

Interplastic Corporation

## Message:

CoREZYN® vinyl ester resins are corrosion resistant to withstand severe environments. In addition, they enhance composites with high-strength, low-weight and excellent resistance to fatigue. That's why our vinyl esters have become the material of choice for many specialized applications, including fire resistance, in industries such as marine, transportation, construction, aerospace and others.

General Information		
Features	Good Corrosion Resistance	
	High Viscosity	
	Medium Reactivity	
Uses	Aerospace Applications	
	Construction Applications	
	Marine Applications	
Additional Information	Nominal Value	Unit
Gel to Peak	1.5 to 4.0	min
Non-Volatile Content	62 to 67	%
Peak Exotherm	171 to 199	°C
Uncured Properties	Nominal Value	Unit
Viscosity (25°C, Brookfield HBT)	2.2 to 2.8	Pa·s
Gel Time <sup>1</sup>	12 to 16	min
NOTE		

1.

SPI gel time run in 180°F (82°C)  
water bath, catalyzed with 1.0 phr  
of 98% benzyol peroxide, minutes.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT