

EVERLON® TAC-50C

Styrene Ethylene Butylene Styrene Block Copolymer

Ever Polymer Co., Ltd.

Message:

Special bonding grade: base on SEBS, with good adhesion for double injection.

All pass by UL certificated

Insert molding: able to bonding with ABS, PC, PC/ABS, PMMA, AS, PBT, PETG, PA (NYLON).

With excellent Weatherability, stability of UV and excellent flexibility.

Suitable for computer, MP3, cell phone, camera, PDA, mouse and so on.

General Information			
Features	Bondability		
	Good Adhesion		
	Good Flexibility		
	Good Weather Resistance		
Uses	Camera Applications		
	Cell Phones		
	Computer Components		
	Electrical Parts		
	Electrical/Electronic Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.898	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	50		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength	7.35	MPa	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Tear Strength	53.9	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-40.0	°C	ASTM D746

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

