Generic CA

Cellulose Acetate

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic CA This information is provided for comparative purposes only.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26 - 1.32	g/cm³	ASTM D792
Water Absorption (23°C, 24 hr)	2.3 - 2.5	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (23°C)	40 - 100		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 23°C	23.4 - 38.0	MPa	ASTM D638
Fracture, 23°C	28.6 - 46.9	MPa	ASTM D638
Tensile Elongation (Yield, 23°C)	25 - 55	%	ASTM D638
Flexural Modulus (23°C)	758 - 1950	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	24.1 - 71.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130 - 330	J/m	ASTM D256
Optical	Nominal Value	Unit	Test Method
Haze	2.9 - 8.5	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	65.3 - 71.1	°C	
Drying Time	2.0 - 3.0	hr	
Rear Temperature	176 - 224	°C	
Middle Temperature	177 - 224	°C	
Front Temperature	177 - 238	°C	
Nozzle Temperature	188 - 216	°C	
Mold Temperature	48.9 - 60.0	°C	
Injection Pressure	7.07 - 14.5	MPa	
Back Pressure	0.172 - 0.224	MPa	
Vent Depth	0.064 - 0.41	mm	
Injection instructions			

This data represents typical values that have been calculated from all products classified as: Generic CAThis information is provided for comparative purposes only.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

