

Bangkok PET V082P

Polyethylene Terephthalate

Bangkok Polyester Public Company Limited

Message:

BANGKOK PET V082P is suitable for the production of bottles for water, edible oil, soy sauce, fruit juice and other packaging applications.

General Information			
Uses	Juice bottle		
	Bottle		
	Food packaging		
Agency Ratings	EEC 128/90		
	FDA 21 CFR 177.1630		
	UK SI 1998 No. 1376		
Forms	Particle		
Processing Method	Injection molding		
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	249	°C	DSC
Additional Information			
Intrinsic Viscosity, Ubbelohde Test Method: 0.80 to 0.84 dl/gMoisture, ASTMD 4019: <0.4 wt-%Colour b-value, Hunter Test Method: <1Acetaldehyde, HS-GC Test Method: <1 ppm			
Injection	Nominal Value	Unit	
Drying Temperature	160 - 180	°C	
Drying Time	4.0 - 6.0	hr	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

