

Milastomer™ W750B

Thermoplastic Vulcanizate

Mitsui Chemicals America, Inc.

Message:

Milastomer™W750B is a thermoplastic vulcanized rubber (TPV) material. This product is available in North America and is processed by blow molding or extrusion.

Milastomer™Typical application areas of W750B are: engineering/industrial accessories

General Information			
Uses	Washer		
	Weather-resistant sealing strip		
Appearance	Black		
Forms	Particle		
Processing Method	Blow molding		
	Extrusion		

Physical	Nominal Value	Unit	Test Method
Density	0.880	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/10.0 kg)	45	g/10 min	ISO 1133

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ISO 48
Shaw A	75		ISO 48
Shaw A, 5 seconds	70		ISO 48

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (100% Strain)	2.80	MPa	ISO 37
Tensile Stress ² (Break)	6.80	MPa	ISO 37
Tensile Elongation ³ (Break)	580	%	ISO 37
Compression Set			ISO 815
23°C, 22 hr	34	%	ISO 815
70°C, 22 hr	47	%	ISO 815

Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -60.0	°C	Internal method

Additional Information			
All tests performed according to Mitsui methods.			

NOTE			
1.	500 mm/min		
2.	500 mm/min		
3.	500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

