

RTP 3400-G-665

Liquid Crystal Polymer

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
-Preliminary Product Data per RTP Co.-

General Information			
Filler / Reinforcement	Glass Fiber		
RoHS Compliance	Contact Manufacturer		
Appearance	Black		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.97	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.020	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	17200	MPa	ASTM D638
Tensile Strength	68.9	MPa	ASTM D638
Tensile Elongation (Break)	0.80	%	ASTM D638
Flexural Modulus	15900	MPa	ASTM D790
Flexural Strength	116	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (3.18 mm)	100	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	224	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	8.0	hr	
Suggested Max Regrind	20	%	
Rear Temperature	332 to 354	°C	
Middle Temperature	332 to 354	°C	
Front Temperature	332 to 354	°C	

Nozzle Temperature	343 to 379	°C
Mold Temperature	65.6 to 121	°C
Injection Pressure	103 to 138	MPa
Clamp Tonnage	5.5 to 11	kN/cm ²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

