

Lumiflon® FE-4300

Fluoropolymer
Asahi Glass Co., Ltd.

Message:

- Applications:
- Architecture
 - Metal
 - Industrial
 - Plastic
 - Repaint

General Information		
Uses	Industrial Applications	
Physical	Nominal Value	Unit
Specific Gravity	1.13	g/cm ³
Average Particle Size - (Diameter)	100 to 500	nm
pH	7.0 to 9.0	
Minimum Film-forming Temperature	35	°C
OH Value	10.0	Mg KOH/g

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT