

RJM SD101G20-F

Polycarbonate

RJM International, Inc.

Message:

RJM SD101G20-F is a Polycarbonate (PC) product filled with 20% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Typical application: Additive/Masterbatch. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Uses	Compounding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	96.1	MPa	ASTM D638
Tensile Elongation (Break)	4.5	%	ASTM D638
Flexural Modulus	5390	MPa	ASTM D790
Flexural Strength	137	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	200	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature	140	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	250 to 310	°C	
Mold Temperature	120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT