

ColorRx® PC-0700RX

Polycarbonate

LTL Color Compounders, Inc.

Message:

A biocompatible, 7 melt extrusion grade Polycarbonate for healthcare applications.

General Information	
Features	Biocompatible
Uses	Medical/Healthcare Applications
Agency Ratings	ISO 10993
	ISO 10993-Part 1
	USP Class VI

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.60 to 0.80	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.12	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	72		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	64.1	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	6.0	%	
Break	110	%	
Flexural Modulus	2310	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	910	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.35 mm)	138	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

