# Geon<sup>™</sup> Vinyl Flexible P484B

### Flexible Polyvinyl Chloride

#### PolyOne Corporation

#### Message:

Geon<sup>™</sup> Vinyl Flexible P484B is a Flexible Polyvinyl Chloride product. It can be processed by extrusion or injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Typical application: Furniture. Characteristics include: High Flow High Gloss

| General Information                     |                     |       |             |
|---|---------------------|-------|-------------|
| Features                                | High Flow           |       |             |
|   | High Gloss          |       |             |
|   |                     |       |             |
| Uses                                    | Furniture           |       |             |
| Appearance                              | Clear/Transparent   |       |             |
| Forms                                   | Pellets             |       |             |
| Processing Method                       | Extrusion           |       |             |
|   | Injection Molding   |       |             |
|   |                     |       |             |
| Physical                                | Nominal Value       | Unit  | Test Method |
| Specific Gravity                        | 1.25                | g/cm³ | ASTM D792   |
| Hardness                                | Nominal Value       | Unit  | Test Method |
| Durometer Hardness (Shore A, 15 sec)    | 85                  |       | ASTM D2240  |
| Mechanical                              | Nominal Value       | Unit  | Test Method |
| Tensile Strength <sup>1</sup> (Break)   | 21.2                | MPa   | ASTM D638   |
| Tensile Elongation <sup>2</sup> (Break) | 380                 | %     | ASTM D638   |
| Thermal                                 | Nominal Value       | Unit  | Test Method |
| Brittleness Temperature                 | -20.0               | °C    | ASTM D746   |
| Injection                               | Nominal Value       | Unit  |             |
| Processing (Melt) Temp                  | 188 to 199          | °C    |             |
| Extrusion                               | Nominal Value       | Unit  |             |
| Melt Temperature                        | 179 to 182          | °C    |             |
| NOTE                                    |                     |       |             |
| 1.                                      | Type IV, 510 mm/min |       |             |
| 2.                                      | Type IV, 510 mm/min |       |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

