

Hostacom PPU X9067HS 151237

Polypropylene Copolymer
LyondellBasell Industries

Message:

Hostacom PPU X9067HS 151237 is an unfilled PP copolymer, with high flowability, superior stiffness and high toughness. Product is available as a customized color matched, pellet form. This grade is delivered in 151237 color version.
This grade is not intended for medical, pharmaceutical, food and drinking water applications.

| General Information | | | |
|---|-------------------|-------------------|-------------|
| Features | Rigid, good | | |
| | Copolymer | | |
| | High liquidity | | |
| | Good toughness | | |
| Appearance | Available colors | | |
| Forms | Particle | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density (23°C) | 0.910 | g/cm ³ | ISO 1183/A |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 13 | g/10 min | ISO 1133 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Stress (Yield, 23°C) | 26.0 | MPa | ISO 527-2 |
| Flexural Modulus ¹ (23°C) | 1450 | MPa | ISO 178/A |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength (23°C) | 10 | kJ/m ² | ISO 179/1eA |
| Charpy Unnotched Impact Strength (23°C) | No Break | | ISO 179/1eU |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 58.0 | °C | ISO 75-2/A |
| Vicat Softening Temperature | 147 | °C | ISO 306/A |
| NOTE | | | |
| 1. | 1.0 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

