

Huaфон JF-W-HE3008A

Polyurethane
Huaфон Group Co., Ltd.

Message:

General Type
Characteristics
Embossing resin, super soft type, high elasticity, sheepskin feeling good, hand down feeling good, good fullness, good film thickness, low-loss rate, uniform cell structure, nonstick surface.
Applications
Garments

General Information		
Features	High Elasticity	
	Non-Stick	
	Soft	
Uses	Textile Applications	
Additional Information	Nominal Value	Unit
Solvents	DMF	
Uncured Properties	Nominal Value	Unit
Solids Content	29 to 31	%
Viscosity (25°C)	160 to 260	Pa·s
Cured Properties	Nominal Value	Unit
Tensile Modulus (100% Secant)	2.00 to 2.50	MPa
Tensile Strength	> 20.0	MPa
Tensile Elongation at Break	> 600	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT