NEFTEKHIM PP 8548S (EPH71HA)

Polypropylene Copolymer

Nizhnekamskneftekhim Inc.

Message:

Product obtained by copolymerization of propylene and ethylene in presence of complex metalorganic catalysts.

It incorporates increased long-term thermal stability, thermal-oxidative degradation resistance when PP is produced, processed and PP-made articles are exploited, antistatic properties to produce and exploit articles, effective nucleation.

Application: dishware, thin-wall package injection molding.

Technical requirements: TU 2211-136-05766801-2006

General Information			
Additive	Antistatic		
	Nucleating Agent		
Features	Antistatic		
	Block Copolymer		
	Good Thermal Stability		
	Nucleated		
	Oxidation Resistant		
Uses	Table Products		
	Thin-walled Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm³	
Apparent Density	0.48 to 0.60	g/cm³	
Melt Mass-Flow Rate (MFR) (230°C/2.16	20. 70		
kg)	38 to 50	g/10 min	ASTM D1238
Ash Content	0.025 to 0.050	%	
Thermal Creep Temperature ¹	64 to 90	°C	
Thermal-oxidative Deterioration (150°C)	15.0	day	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	40 to 88		
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1350	МРа	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	50	J/m	ASTM D256
Thermal	Nominal Value	Unit	
Vicat Softening Temperature ²	126 to 150	°C	

1. at load 0.46 H/mm²

2. in liquid medium under force 10 H

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

