

LAPEROS® T150

Liquid Crystal Polymer

Polyplastics Co., Ltd.

Message:

Ultra-High Heat Resistant, High MP, Glass fiber reinforced, High stiffness

General Information			
UL YellowCard	E106764-472588		
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Features	High Heat Resistance		
	High Stiffness		
UL File Number	E106764		
Part Marking Code (ISO 11469)	>LCP-GF50<		
Physical	Nominal Value	Unit	Test Method
Density	1.81	g/cm ³	ISO 1183
Molding Shrinkage ¹			Internal Method
Across Flow : 1.00 mm	0.42	%	
Flow : 1.00 mm	0.060	%	
Water Absorption (23°C, 24 hr)	0.040	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	55		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	125	MPa	ASTM D638
Tensile Elongation (Break)	1.1	%	ASTM D638
Flexural Modulus	19500	MPa	ISO 178
Flexural Stress	200	MPa	ISO 178
Flexural Strain	1.6	%	ISO 178
Color Number	BK005P		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	12	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	295	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.0E+16	ohms · cm	IEC 60093
Electric Strength			IEC 60243-1
1.00 mm	40	kV/mm	
3.00 mm	28	kV/mm	
Dielectric Constant			IEC 60250

1 kHz	4.70		
1 MHz	4.30		
Dissipation Factor			IEC 60250
1 kHz	0.010		
1 MHz	0.020		
Arc Resistance	155	sec	
Comparative Tracking Index	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
NOTE			
1.	80x80x1 mm; Inj. Pressure 60MPa		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT