RTP 2800B-50D HF

Thermoplastic Vulcanizate

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'

The data for this material has not been recently verified.

Please contact RTP Company for current information prior to specifying this grade.

| General Information | | | |
|---|----------------------|-------|-------------|
| Features | High Flow | | |
| RoHS Compliance | Contact Manufacturer | | |
| Appearance | Black | | |
| | Natural Color | | |
| F | Dallana | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.968 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow (3.18 mm, Injection Molded) | 1.5 | % | ASTM D955 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D) | 50 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 17.0 | МРа | ASTM D412 |
| Tensile Elongation (Break) | 750 | % | ASTM D412 |
| Tear Strength ¹ | 79.0 | kN/m | ASTM D624 |
| Injection | Nominal Value | Unit | |
| Rear Temperature | 171 to 199 | °C | |
| Middle Temperature | 171 to 199 | °C | |
| Front Temperature | 171 to 199 | °C | |
| Mold Temperature | 16.0 to 66.0 | °C | |
| Injection Pressure | 83.0 to 124 | МРа | |
| NOTE | | | |
| 1. | Die C | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

