Dryflex® 502450S

Styrene Ethylene Butylene Styrene Block Copolymer

ELASTO

Message:

The 500S series is very favourable when transparency and good scratch resistance are required, as well as when there are high surface finish requirements. Unfilled grades have excellent flow and mechanical properties, such as elongation, compression set, tensile and tear strength. The low density entails lower weight compared to the 600S and 660S series. Unfilled compounds are available in hardness from 0 Shore A to 55 Shore D in translucent and black colours but they can easily be coloured in any shade.

General Information							
Features	Bondability Food Contact Acceptable Good Chemical Resistance Good Weather Resistance						
					Scratch Resistant		
Appearance	Black						
Physical	Nominal Value	Unit	Test Method				
Specific Gravity	0.890	g/cm³	ASTM D792				
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238				
Molding Shrinkage	0.80 to 2.0	%					
Hardness	Nominal Value	Unit	Test Method				
Durometer Hardness (Shore A)	45		ASTM D2240				
Mechanical	Nominal Value	Unit	Test Method				
Tensile Strength			ASTM D638				
	6.00	MPa					
100% Strain	1.00	MPa					
300% Strain	2.00	MPa					
Tensile Elongation (Break)	> 600	%	ASTM D638				
Elastomers	Nominal Value	Unit	Test Method				
Tear Strength	18.0	kN/m	ASTM D624				
Compression Set (23°C, 72 hr)	10	%	ASTM D395				
Thermal	Nominal Value	Unit					
Service Temperature	-50 to 125	°C					
Injection	Nominal Value	Unit					
Processing (Melt) Temp	180 to 210	°C					

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

