

Generic Silicone - Unspecified

Silicone

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic Silicone - Unspecified
This information is provided for comparative purposes only.

General Information			
Filler / Reinforcement	Filler		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	0.345 to 2.41	MPa	ASTM D638
Uncured Properties	Nominal Value	Unit	
Density (23°C)	0.868 to 1.12	g/cm ³	
Viscosity (23°C)	0.095 to 0.77	Pa·s	
Curing Time (23°C)	2.0 to 1.7E+2	hr	
Cured Properties	Nominal Value	Unit	
Shore Hardness (23°C)	15 to 40		
Tensile Strength (23°C)	0.517 to 12.4	MPa	
Tensile Elongation at Break (23°C)	350 to 1000	%	
Tear Strength (23°C)	2.10 to 52.5	kN/m	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT