

RTP 799 X 144652 B EG

High Density Polyethylene
RTP Company

Message:
ESD Protection - Extrusion Grade - Preliminary Datasheet

General Information			
Features	Electrostatic discharge protection		
RoHS Compliance	Contact manufacturer		
Processing Method	Extrusion		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	< 1.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	1.0 - 3.0	%	ASTM D955

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1380	MPa	ASTM D638
Tensile Strength	27.6	MPa	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	1240	MPa	ASTM D790
Flexural Strength	34.5	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	53	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	1200	J/m	ASTM D4812

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+6 - 1.0E+12	ohms	ASTM D257
Volume Resistivity	1.0E+5 - 1.0E+10	ohms · cm	ASTM D257

Injection	Nominal Value	Unit
Injection Pressure	68.9 - 103	MPa

Extrusion	Nominal Value	Unit
Drying Temperature	79	°C
Drying Time	2.0	hr
Melt Temperature	193 - 232	°C
Die Temperature	21 - 66	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

