

ESTAPROP K 1060 TG

Polypropylene Copolymer

Cossa Polimeri S.r.l.

Message:

ESTAPROP K 1060 TG is a Polypropylene Copolymer (PP Copolymer) product filled with 30% filler. It is available in Europe. Typical application: Automotive.

Characteristics include:

- Flame Rated
- Copolymer
- Impact Resistant

General Information			
Filler / Reinforcement	Filler,30% Filler by Weight		
Features	Copolymer		
	Good Impact Resistance		
	Paintable		
Uses	Automotive Applications		
Appearance	Opaque		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.80 to 1.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	15.0	MPa	ASTM D638
Tensile Elongation (Yield)	15	%	ASTM D638
Flexural Modulus	2400	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	40	J/m	
23°C	100	J/m	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	60.0	°C	ASTM D1525 ¹
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
NOTE			
1.	Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

