

OmniCarb™ PC/PBT 1214 IM

Polycarbonate + PBT
OMNI Plastics, LLC

Message:
Impact Modified, PC/PBT Alloy

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage	0.40 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	62.1	MPa	ASTM D638
Tensile Elongation (Break)	120	%	ASTM D638
Flexural Modulus	2480	MPa	ASTM D790
Flexural Strength	88.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	750	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	104	°C	
1.8 MPa, Unannealed, 3.18 mm	93.3	°C	
Flammability	Nominal Value	Test Method	
Flame Rating (3.18 mm)	HB	Internal Method	
Injection	Nominal Value	Unit	
Drying Temperature	110	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	249 to 271	°C	
Middle Temperature	249 to 282	°C	
Front Temperature	249 to 282	°C	
Nozzle Temperature	249 to 282	°C	
Processing (Melt) Temp	249 to 271	°C	
Mold Temperature	48.9 to 82.2	°C	
Back Pressure	0.345 to 0.689	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

