

KPOL-NYLON K-NY6/27D

Polyamide 6
KPOL Chem Co.

Message:

Standard Polyamide 6
Applications
General purpose, Injection Molding and Extrusion/Molding applications.
Characteristics
Exhibit excellent melt flow properties for filling thin sections and reduced cycle times. It exhibits good set of mechanical properties, strength, stiffness, and toughness as well as excellent heat, chemical and abrasion resistance.

General Information			
Features	Good Abrasion Resistance		
	Good Chemical Resistance		
	Good Stiffness		
	Good Strength		
	Good Toughness		
	High Flow		
	High Heat Resistance		
Uses	General Purpose		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Water Absorption (Equilibrium)	1.2	%	ASTM D570
Relative Viscosity ¹	2.8		ASTM D789
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	78.0	MPa	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	56	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	222	°C	ASTM D2117
NOTE			

1. SAV @ 98% Sulfuric Acid

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

