

ADDINYL A2I V25

Polyamide 66

ADDIPLAST

Message:

ADDINYL A2I V25 is a Polyamide 66 (Nylon 66) material filled with 25% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America.

Important attributes of ADDINYL A2I V25 are:

Flame Rated
Flame Retardant
Halogen Free

Typical applications include:

Automotive
Electrical/Electronic Applications
Wire & Cable

General Information				
Filler / Reinforcement		Glass Fiber,25% Filler by Weight		
Additive		Flame Retardant		
Features		Flame Retardant		
		Halogen Free		
Uses		Automotive Applications		
		Electrical/Electronic Applications		
		Telecommunications		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.37	--	g/cm ³	ISO 1183/A
Hardness	Dry	Conditioned	Unit	Test Method
Shore Hardness (Shore D)	90	89		ISO 868
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress (Break)	130	90.0	MPa	ISO 527-2
Tensile Strain (Break)	5.0	6.0	%	ISO 527-2
Flexural Modulus	7800	5500	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	8.5	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	60	60	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	8.5	9.5	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	245	--	°C	ISO 75-2/Af

Melting Temperature (DSC)	260	--	°C	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	V-0	--		UL 94
Glow Wire Ignition Temperature	960	--	°C	IEC 60695-2-13
Oxygen Index	32	--	%	ISO 4589-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

