

# MarFlex® 7308FK

Linear Low Density Polyethylene  
Chevron Phillips Chemical Company LLC

Message:

MarFlex® 7308FK is a linear low density polyethylene material. This product is available in North America or Latin America. The processing method is blow molded film.

MarFlex® The main features of 7308FK are:

Antiblock software  
slide  
hexene comonomer  
Good processability  
processing aids  
Typical application areas include:  
bag/lining  
packing  
Movie  
industrial applications  
additive/masterbatch

General Information			
Additive	Low caking resistance		
	High smoothness		
	Processing aid		
Features	Low caking resistance		
	Rigid, good		
	High smoothness		
	hexene comonomer		
	Workability, good		
	Good toughness		
	General		
Uses	Packaging		
	Films		
	Industrial application		
	Mixing		
	General		
	Heavy packing bag		
Forms	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.925	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.80	g/10 min	ASTM D1238

Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (Blown Film)	0.15		ASTM D1894
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
1% secant, MD: 25 µm, blown film	290	MPa	ASTM D882
1% secant, TD: 25 µm, blown film	345	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Broken, 25 µm, blown film	55.0	MPa	ASTM D882
TD: Broken, 25 µm, blown film	34.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 25 µm, blown film	400	%	ASTM D882
TD: Broken, 25 µm, blown film	700	%	ASTM D882
Dart Drop Test - Blown Film (25.4 µm)	48.3	kN/m	ASTM D1709
Elmendorf Tear Strength <sup>1</sup>			ASTM D1922
MD : 25.4 µm	115.8	kN/m	ASTM D1922
TD : 25.4 µm	251.0	kN/m	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Gloss (60°, 25.4 µm, Blown Film)	65		ASTM D2457
Haze (25.4 µm, Blown Film)	18	%	ASTM D1003
Additional Information			
Blown Film produced on 3.5 in extruder, 30:1 L/D, 8 in Die, 80 mil Die Gap, 2.5:1 BUR, 440°F Melt Temperature.			
NOTE			
1.	Blown Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT