

HIDEN® M830

High Density Polyethylene

YUHWAW Korea Petrochemical Ind. Co., Ltd.

Message:

HIDEN® M830 is a High Density Polyethylene material. It is available in Asia Pacific for injection molding.

Important attributes of HIDEN® M830 are:

RoHS Compliant

Impact Resistant

Rigid

Typical applications include:

Containers

Food Contact Applications

Industrial Applications

General Information			
Features	High Impact Resistance		
	High Rigidity		
Uses	Containers		
	General Purpose		
	Industrial Applications		
Agency Ratings	FDA Food Contact, Unspecified Rating		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.962	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.8	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.5 to 2.5	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	54		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	27.5	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	1180	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	200	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	125	°C	ASTM D1525
Peak Melting Temperature	135	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

