

KEP® 2320

Ethylene Propylene Diene Terpolymer

Kumho Polychem Co., Ltd.

Message:

Features:

Excellent roll processability, good processing even without oil, excellent extrusion, fast cure, good electrical property

Applications:

Electrical insulation, brake parts, gaskets, corner molding, molded sponge

General Information		
Features	Fast Cure	
	Good Electrical Properties	
	Good Processability	
Uses	Electrical/Electronic Applications	
	Electronic Insulation	
	Gaskets	
Forms	Bale	
Processing Method	Extrusion	
	Injection Molding	
Physical	Nominal Value	Unit
Mooney Viscosity (ML 1+4, 125°C)	25	MU
Ethylene Content	58.0	wt%
Ethylidene Norbornene (ENB) Content	4.7	wt%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT