

Jamplast JP70G33

Polyamide 66

Jamplast, Inc.

Message:

Jamplast JP70G33 is a Polyamide 66 (Nylon 66) material filled with 33% glass fiber. It is available in North America for injection molding. Primary attribute of Jamplast JP70G33: Hydrolytically Stable.

Typical applications include:

- Appliances
- Automotive
- Electrical/Electronic Applications
- Industrial Applications

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Features	Hydrolytically Stable		
Uses	Appliance Components		
	Automotive Applications		
	Electrical/Electronic Applications		
	Industrial Applications		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	124	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	4.0	%	ASTM D638
Flexural Modulus (1850 mm)	6210	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130	J/m	ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT