

# Hyflon® PFA P125

Perfluoroalkoxy

Solvay Specialty Polymers

## Message:

Hyflon® PFA is a unique family of semi-crystalline, melt processable perfluoropolymers which combine excellent mechanical characteristics to unique properties such as chemical inertness, heat resistance, inherent flame resistance, low surface energy, and exceptional dielectric properties. Hyflon® PFA resins have been designed to retain their properties over a wide range of temperatures from cryogenic to 300°C (572°F)\* and are the material of choice in applications such as linings in the chemical process industry, specialty cables, semiconductor industry, aerospace, and other challenging industries.

Hyflon® PFA P125 is a low melt flow rate perfluoroalkoxy resin designed for enhanced creep resistance, higher long-term pressure resistance, and excellent thermal stability. It is a Type II PFA according to ASTM D 3307.

\* For rating at 300°C (572°F) contact your Solvay Representative.

General Information			
Features	Semicrystallization		
	Low liquidity		
	Heat resistance, high		
	Flame retardancy		
Uses	Semiconductor molding compound		
	Lining		
	Cable sheath		
	Piping system		
	Pipe fittings		
	Aerospace applications		
Agency Ratings	ASTM D 3307 Type II		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (372°C/5.0 kg)	1.5 - 3.0	g/10 min	ASTM D1238
Density	2.120 - 2.170	g/cm <sup>3</sup>	ASTM D792
Heat of crystallization	28.0 - 38.0	J/g	ASTM D4591
Heat of Fusion	28.0 - 38.0	J/g	ASTM D4591
Linear expansion coefficient	1.2E-4 - 2.0E-4	cm/cm/°C	ASTM D696
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	55 - 60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup> (23°C)	500 - 600	MPa	ASTM D1708
Tensile Strength (Break, 23°C)	> 25.0	MPa	ASTM D1708
Tensile Elongation (Break, 23°C)	> 300	%	ASTM D1708
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength (23°C)	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	310 - 316	°C	ASTM D4591
Peak Crystallization Temperature (DSC)	285 - 295	°C	ASTM D4591
Specific Heat (23°C)	900 - 1100	J/kg/°C	ASTM E1269
Thermal Conductivity (40°C)	0.15 - 0.25	W/m/K	ASTM C177
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	95	%	ASTM D2863
Additional Information			
<p>PROCESSINGBecause PFA is corrosive in the melt, machinery used to process Hyflon® should be lined with corrosion resistant alloys.HEALTH SAFETY AND ENVIRONMENTHyflon® PFA P125 is a very inert polymer and it is not harmful if used and handled according to standard processing procedures.If handled inappropriately, it may release harmful toxic chemicals. Please refer to the Material Safety Data Sheets for more information on handling and safety.PACKAGING AND STORAGEHyflon® PFA P125 resin is available in 25 kg (55 lbs) and 600 kg (1323 lbs) packaging. Though it has an indefinite shelf life, it is recommended to store it in a clean area, protected from direct sunlight, and possible contamination.</p>			
NOTE			

1. 1.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT