

Polifil® Nylon 1080

Polyamide 612
The Plastics Group

Message:
Polifil® Nylon 1080 is a Polyamide 612 (Nylon 612) product. It is available in North America.

General Information		
Features	General Purpose	
Forms	Pellets	
Injection	Nominal Value	Unit
Rear Temperature	238	°C
Middle Temperature	229	°C
Front Temperature	227	°C
Nozzle Temperature	232	°C
Processing (Melt) Temp	232 to 288	°C
Injection Rate	Moderate-Fast	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT