

RTP 306 TFE 20

Polycarbonate
RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
-Preliminary Product Data per RTP Co.-
The value listed as Flammability, UL 94, was tested in accordance with RTP test standards.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 35% filler by weight		
Additive	PTFE lubricant (20%)		
Features	Good dimensional stability		
	Good wear resistance		
	Lubrication		
	Self-lubricating		
Uses	Gear		
	Cam		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.61	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.060	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8960	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	96.5	MPa	ASTM D638
--	96.5	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Flexural Strength			ASTM D790

--	145	MPa	ASTM D790
Yield	145	MPa	ASTM D790
Compressive Strength	93.1	MPa	ASTM D695
Coefficient of Friction (With Metal-Dynamic)	0.18		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	96	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	430	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	149	°C	ASTM D648
1.8 MPa, not annealed	143	°C	ASTM D648
CLTE - Flow	2.3E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.32	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	18	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.40		ASTM D150
Dissipation Factor (1 MHz)	7.0E-3		ASTM D150
Arc Resistance (3.18 mm)	120	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.18 mm)	V-0		UL 94
Additional Information			
Mold Shrinkage, Linear-Flow, ASTM D-955, 0.25in.: 2mil/in.The coefficient of friction was tested on a Falex Model No.6 Wear Testing Machine at 50 FPM, 2000 PV, against C1018 steel of hardness 15-25 Rockwell C, 14-17 micro smoothness.			
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Max Regrind	20	%	
Rear Temperature	288 - 343	°C	
Middle Temperature	288 - 343	°C	
Front Temperature	288 - 343	°C	
Mold Temperature	65.6 - 121	°C	
Injection Pressure	68.9 - 103	MPa	
Back Pressure	0.172 - 0.345	MPa	
Screw Speed	50 - 90	rpm	
Clamp Tonnage	6.9 - 11	kN/cm ²	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

