

Spartech Polycom PP5410UV D84

Polypropylene
Spartech Polycom

Message:

10% Glass Reinforced, Chemically Coupled, UV Stabilized, Polypropylene, White compound offers a superior level of stiffness and heat deflection performance. This product is suitable for injection molding processes. A Spartech Polycom representative can provide further information on this and other Spartech Polycom products.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Features	Rigid, good		
	Good UV resistance		
	Heat resistance, high		
Appearance	White		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.998	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (224°C/2.16 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	55.2	MPa	ASTM D638
--	44.8	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	3.0	%	ASTM D638
Fracture	3.0	%	ASTM D638
Flexural Modulus - Secant	2210	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	146	°C	ASTM D648
1.8 MPa, not annealed	124	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

