POWERSIL® GEL FC A/B

Silicone

Wacker Chemie AG

General Information

Message:

Silicone Gel Instrumentation & Control Cables, Cable Industry Cables for Household Appliances, Cable Industry

Features	Electrically Insulating						
Uses	Bushings Extra High Voltage Insulation High Voltage Insulation Insulation Low Voltage Insulation Medium Voltage Insulation						
				Processing Method	Encapsulating		
					Potting		
Uncured Properties	Nominal Value	Unit	Test Method				
Color	Clear/Transparent						
Density	0.970	g/cm³	ISO 1183				
Viscosity	1.0	Pa·s	ISO 3219				
Pot Life	20	min					
Cured Properties	Nominal Value	Unit	Test Method				

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

kV/mm

IEC 60243

IEC 60250

IEC 60250

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

23

2.50

2.0E-4

Tel: +86 21 5895 8519

Electric Strength

Relative Permittivity

Dissipation Factor (50 Hz)

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

