

Gallonprene® GP640-9501

Thermoplastic Elastomer

Shenzhen Sungallon Rubber & Plastic Corporation Limited

Message:

Gallonprene® GP640-9501 is a thermoplastic elastomer (TPE) product. It can be processed by injection molding and is available in Africa and the Middle East, Latin America or Asia Pacific. Typical application areas are: engineering/industrial accessories.

Features include:

Comply with REACH standard

ROHS certification

Flame Retardant

Halogen-free

General Information			
Additive	Flame retardancy		
Features	High elasticity		
	Halogen-free		
	Flame retardancy		
Uses	overmolding		
	Plug		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Appearance	White		
	Rough surface polishing		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/10.0 kg)	55	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 23°C)	95		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	8.00	MPa	ASTM D412
Tensile Elongation ² (Break)	600	%	ASTM D412
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Rear Temperature	160 - 180	°C	
Middle Temperature	170 - 190	°C	
Front Temperature	180 - 200	°C	

Processing (Melt) Temp	140 - 160	°C
Mold Temperature	30.0 - 60.0	°C
Injection Rate	Fast	

Injection instructions

Processing Temperature Limit: 240°CInjection Pressure: HighBack Pressure: 20 to 50%Overmolding Parameters:Rear Temperature: 170 to 190°CCenter Temperature: 180 to 200°CFront Temperature: 190 to 210°CMelt Temperature: 140 to 160°C Mold Temperature: 30 to 60°CProcessing Temperature Limit: 240°CInjection Pressure: HighInjection Speed: HighBack Pressure: 20 to 50%Drying Temperature: 80°C Drying Time: 2 hr

NOTE

1.	500 mm/min
2.	500 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

