

Delrin® 100PE NC010

ACETAL RESIN

DuPont Performance Polymers

Message:

High Viscosity Acetal Homopolymer with Very Low Emissions

General Information			
Additive	Mold Release		
Uses	Profiles		
	Sheet		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
	Profile Extrusion		
	Sheet Extrusion		
Multi-Point Data	Shear Stress vs. Shear Rate (ISO 11403-1)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Part Marking Code (ISO 11469)	>POM<		
Resin ID (ISO 1043)	POM		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.5	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	2.10	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.8	%	
Flow	2.2	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ISO 2039-2
M-Scale	91		
R-Scale	121		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3100	MPa	ISO 527-2
Tensile Stress (Yield)	72.0	MPa	ISO 527-2
Tensile Strain (Yield)	26	%	ISO 527-2
Nominal Tensile Strain at Break	45	%	ISO 527-2
Flexural Modulus	2900	MPa	ISO 178

Flexural Stress (3.5% Strain)	79.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	13	kJ/m ²	
23°C	15	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	400	kJ/m ²	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	157	°C	ISO 75-2/B
1.8 MPa, Unannealed	99.0	°C	ISO 75-2/A
Melting Temperature ¹	178	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	1.1E-4	cm/cm/°C	
Flow : -40 to 23°C	1.0E-4	cm/cm/°C	
Transverse	1.1E-4	cm/cm/°C	
Transverse : -40 to 23°C	1.0E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	3.0E+14	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength	44	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.00		
1 MHz	3.90		
Dissipation Factor			IEC 60250
100 Hz	5.0E-4		
1 MHz	5.0E-3		
Comparative Tracking Index	600	V	IEC 60112
Fill Analysis	Nominal Value	Unit	Test Method
Melt Density	1.19	g/cm ³	
Additional Information	Nominal Value	Unit	Test Method
Emission	< 2.00	mg/kg	VDA 275
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

