

RTP 154 HF

Polypropylene
RTP Company

Message:
High Flow - Flame Retardant

General Information			
UL YellowCard	E84658-101913882		
Features	Flame Retardant		
	High Flow		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20 to 25	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	1.5 to 2.0	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.010	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1590	MPa	ASTM D638
Tensile Strength	29.0	MPa	ASTM D638
Tensile Elongation (Break)	> 100	%	ASTM D638
Flexural Modulus	1380	MPa	ASTM D790
Flexural Strength	40.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	27	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	1000	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	48.9	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms · cm	ASTM D257
Dielectric Strength ¹ (in Oil)	31	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	UL 94		
0.800 mm	V-0		
0.200 mm	VTM-0		
Oxygen Index	28	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	

Drying Time	2.0	hr
Processing (Melt) Temp	191 to 232	°C
Mold Temperature	32.2 to 65.6	°C
Injection Pressure	68.9 to 103	MPa

NOTE

1.
- Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT