Novalloy-S S1500

Polycarbonate + ABS

PlastxWorld Inc.

Message:

Novalloy - S~S1500~is~a~Polycarbonate~+~ABS~(PC+ABS)~product.~It~can~be~processed~by~injection~molding~and~is~available~in~Europe.

Characteristics include: Heat Resistant

Impact Resistant

General Information			
Features	High Heat Resistance		
	High Impact Resistance		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (240°C/5.0 kg)	5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	51.7	MPa	ASTM D638
Tensile Elongation (Break)	80	%	ASTM D638
Flexural Modulus	2160	MPa	ASTM D790
Flexural Strength	87.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	590	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8			
MPa, Unannealed)	120	°C	ASTM D648
Vicat Softening Temperature	126	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

