

MAJORIS CE141 - 8229

Polyolefin

AD majoris

Message:

CE141 - 8229 is a polyolefin compound mineral filled for injection moulding.

The product is available in black (CE141 - 8229) and natural (CE141) but other colours can be provided on request.

CE141 - 8229 has been developed for applications with good impact strength and heat stability.

APPLICATIONS

CE141 - 8229 is intended for components which require good impact strength, dimensional stability.

Suitable applications are:

Electrical tool and appliance components

Miscellaneous automotive technical items

Electrical parts

General Information			
Filler / Reinforcement	Mineral filler, 10% filler by weight		
Features	Good dimensional stability		
	Impact resistance, high		
	Recyclable materials		
	Thermal stability, good		
Uses	Electrical/Electronic Applications		
	Electrical components		
	Power/other tools		
	Home appliance components		
	Application in Automobile Field		
Appearance	Black		
	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.966	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1200	MPa	ISO 527-2/1
Tensile Stress (Yield)	22.0	MPa	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	22	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU

Injection	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	3.0	hr
Processing (Melt) Temp	220 - 250	°C
Mold Temperature	30.0 - 50.0	°C
Injection Rate	Slow-Moderate	

Injection instructions

Holding pressure: 50 to 70% of the injection pressure

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

