Hifax BA35H

Polypropylene Copolymer LyondellBasell Industries

Message:

Hifax BA35H conventional melt flow, 1,000 MPa flexural modulus, UL 94 V-2 flame retardant polypropylene copolymer has an excellent combination of properties and processability. It was designed for applications that require flame and heat resistance, along with good electrical properties, high impact strength and good surface quality.

General Information					
Additive	Flame Retardant				
Features	Copolymer				
	Flame Retardant				
	Good Colorability				
	Good Corrosion Resistance				
	Good Electrical Properties				
	Good Impact Resistance				
	Good Processability				
	Good Surface Finish				
	High Heat Resistance				
	Medium Flow				
Uses	Battery Cases				
	Furniture				
	Household Goods				
	Industrial Applications				
Forms	Pellets				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Melt Mass-Flow Rate (MFR) (230°C/2.16					
kg)	4.0	g/10 min	ASTM D1238		
Molding Shrinkage - Flow (23°C, 48 hr, 3.20 mm, Injection Molded)	1.5	%	ASTM D955		
Hardness	Nominal Value	Unit	Test Method		
Rockwell Hardness (R-Scale)	85		ASTM D785		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield)	27.0	МРа	ASTM D638		
Tensile Elongation (Break)	85	%	ASTM D638		
Flexural Modulus	1000	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (23°C)	130	J/m	ASTM D256		

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	88.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	8.9E+16	ohms·cm	ASTM D257
Dielectric Strength	27	kV/mm	ASTM D149
Arc Resistance	133	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-2		UL 94
Oxygen Index	28	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

