

Geon™ BIO RC9000

Flexible Polyvinyl Chloride

PolyOne Corporation

Message:

A flexible vinyl formulated to achieve a minimum level of 25% bio-based content and classified as a PolyOne Sustainable Solution

General Information			
Features	Non-Phthalate Plasticizer		
	Renewable Resource Content		
Uses	Building Materials		
	Consumer Applications		
	Industrial Applications		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	92		
Shore A, 15 sec	86		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Break	15.4	MPa	
100% Strain	10.0	MPa	
Tensile Elongation ² (Break)	320	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-24.7	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	23	%	ASTM D2863
Injection	Nominal Value	Unit	
Processing (Melt) Temp	188 to 199	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	171 to 182	°C	
NOTE			
1.	510 mm/min		
2.	510 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

