## SIBUR Synthetic Rubber NBR 3330

Acrylonitrile Butadiene Rubber

## SIBUR, LLC

## Message:

NBR 3330, NBR 3335 are essentially an acrylonitrile (31-35 %) and 1,3-butadiene copolymer obtained by emulsion polymerization method at a temperature with the use of fatty acid soaps as emulsifier in accordance with the ecologically clean technology. Medium content of acrylonitrile, heightened oil resistance.

Product characteristics: Appearance - bales of light-yellow to pink or light-beige color depending on used antioxidant; weight of a bale -  $(30 \pm 1)$  kg; packing - a plastic container 540 or 450 kg; shelf life - one (1) year since the date of manufacture.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Oil Resistant		
Appearance	Yellow		
Forms	Bale 2		
Physical	Nominal Value	Unit	Test Method
Mooney Viscosity (ML 1+4, 100°C)	27 to 33	MU	Internal Method
Acrylonitrile Content	31.0 to 35.0	%	Internal Method
Ash Content	< 0.50	%	Internal Method
Volatile Matter	< 0.80	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 22.5	MPa	Internal Method
Tensile Elongation (Break)	> 450	%	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

