

SEPAZ™ 335TS

Polyphthalamide

Mando Advanced Materials Co., Ltd.

Message:

SEPAZ™ 335TS is a Polyphthalamide (PPA) product filled with 35% glass fiber. It is available in Asia Pacific.

Characteristics include:

- Flame Rated
- Heat Resistant
- Low Moisture Absorption

| General Information | | | |
|---|----------------------------------|-------------------|-------------|
| Filler / Reinforcement | Glass Fiber,35% Filler by Weight | | |
| Features | High Heat Resistance | | |
| | Low Moisture Absorption | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.49 | g/cm ³ | ASTM D792 |
| Molding Shrinkage ¹ | | | ASTM D955 |
| Flow | 0.40 | % | |
| Across Flow | 0.80 | % | |
| Water Absorption (24 hr) | 0.21 | % | ASTM D570 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 191 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 2.0 | % | ASTM D638 |
| Flexural Modulus | 12300 | MPa | ASTM D790 |
| Flexural Strength | 270 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 91 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 280 | °C | ASTM D648 |
| Peak Melting Temperature | 313 | °C | ASTM D2133 |
| Flammability | Nominal Value | | Test Method |
| Flame Rating | HB | | UL 94 |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 300 to 330 | °C | |
| Mold Temperature | 130 to 160 | °C | |
| NOTE | | | |
| 1. | 60°C Mold Temperature | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT