

GAPEX® HT RNP38MU05BK

Polyamide + PP

Ferro Corporation

Message:

GAPEX® HT RNP38MU05BK is a Polyamide + PP (Nylon+PP) material filled with 38% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Typical application of GAPEX® HT RNP38MU05BK: Automotive

General Information			
Filler / Reinforcement	Glass Fiber,38% Filler by Weight		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (275°C/5.0 kg)	23	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	0.30	%	
Across Flow	0.90	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	159	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	4.5	%	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 23°C	9000	MPa	
Tangent : 23°C	9310	MPa	
Flexural Strength (23°C)	236	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	150	J/m	ASTM D256
Unnotched Izod Impact (23°C)	1100	J/m	ASTM D256
Gardner Impact	0.904	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	246	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT